

Role of atomic and molecular nitrogen in carbon nanotube formation

Duy D.Q., Kim H.S., Yoon D.M., Ha J.W., Lee K.J., Hwang Y.G., Lee C.H., Cong B.T.

Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749; Faculty of Physics, Hanoi University of Science, Vietnam National University, 334 Nguyen Trai, Thanh Xuan, Hanoi, Viet Nam

Abstract: We have investigated the pretreatment effects of nitrogen on the length and the alignment of carbon nanotubes (CNTs) grown on a Ni catalyst by using dc-plasma enhanced chemical vapor deposition system. The surface of the Ni catalyst was pretreated with a mixture of NH₃ and N₂, instead of pure NH₃ and the length of the CNTs has changed from 1.6 μm to 400 nm as the NH₃/N₂ flow rate ratio was decreased. We showed that the length and the alignment of the CNTs could be controlled by changing the NH₃/N₂ flow rate ratio. The fabricated CNTs were further evaluated by using their Raman spectra. The nitrogen concentration on the surface of the Ni catalyst after the pre-treatment was analyzed by using X-ray photoelectron spectroscopy and the physical structure of CNTs was analyzed using scanning electron microscopy and high resolution transmission electron microscope. We suggest that the N₂ adsorption on the surface of Ni changes the carbon atom diffusion during the CNT growth and that the physical structures of CNTs are drastically changed.

Author Keywords: Cnts; PECVD; Pretreatment; XPS

Year: 2009

Source title: Journal of the Korean Physical Society

Volume: 54

Issue: 4

Page : 1554-1558

Link: Scopus Link

Correspondence Address: Lee, C. H.; Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749; email: chlee@wonkwang.ac.kr

ISSN: 3744884

DOI: 10.3938/jkps.54.1554

Language of Original Document: English

Abbreviated Source Title: Journal of the Korean Physical Society

Document Type: Article

Source: Scopus

Authors with affiliations:

- Duy, D.Q., Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749
- Kim, H.S., Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749

- Yoon, D.M., Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749
- Ha, J.W., Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749
- Lee, K.J., Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749
- Hwang, Y.G., Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749
- Lee, C.H., Regional Innovation Center for Next Generation Industrial Radiation Technology, Division of Microelectronics and Display Technology, Wonkwang University, Iksan 570-749
- Cong, B.T., Faculty of Physics, Hanoi University of Science, Vietnam National University, 334 Nguyen Trai, Thanh Xuan, Hanoi, Viet Nam

References:

- Iijima, S., (1991) Nature, 354, p. 56
- Bonard, J.M., Kind, H., Stöckli, T., Nilsson, L., (2001) Solid-State Electron., 45, p. 893
- Choi, W.B., Jung, D.S., Kang, J.H., Kim, H.Y., Jin, Y.W., Han, I.T., Lee, Y.H., Kim, J.M., (1999) Appl. Phys. Lett., 75, p. 3129
- Robertson, J., (2007) Materials Today, 10, p. 36
- Gibson, C.T., Carnally, S., Roberts, C.J., (2007) Ultramicroscopy, 107, p. 1118
- Schlapbach, L., Zuttel, A., (2001) Nature, 353, p. 414
- Collins, P.G., Bradley, K., Ishigami, M., Zettl, A., (2000) Science, 287, p. 1801
- Fan, S.S., Chapline, M.G., Franklin, N.R., Tomber, T.W., Cassell, A.M., Dai, H.J., (1999) Science, 283, p. 512
- Cui, S., Sharff, P., Siegmund, C., Schneider, D., Risch, K., Klötzer, S., Spiess, L., Schawohl, J., (2004) Carbon, 42, p. 931
- Huang, Z.P., Xu, J.W., Ren, Z.F., Wang, J.H., Siegal, M.P., Provencio, P.N., (1998) Appl. Phys. Lett., 73, p. 3845
- Yudasaka, M., Kikuchi, R., Matsui, T., Ohki, Y., Yoshimura, S., (1995) Appl. Phys. Lett., 67, p. 2477
- Ren, Z.F., Huang, Z.P., Xu, J.W., Wang, J.H., Bush, P., Siegal, M.P., Provencio, P.N., (1998) Science, 282, p. 1105
- Moon, J.H., Lim, S.H., Park, K.C., Jang, J., Kang, S.G., Bae, W.K., Kim, J.J., Lee, C.H., (2004) J. Korean Phys. Soc., 45, p. 1165
- Teo, K.B.K., Chhowalla, M., Amaratunga, G.A.J., Milne, W.I., Hasko, D.G., Pirio, G., Legagneux, P., Pribat, D., (2001) Appl. Phys. Lett., 79, p. 1534
- Mårtensson, N., Nilsson, A., (1990) J. Electron Spectrosc. Rel. Phenom., 52, p. 1
- Egelhoff, W.F., (1984) Surf. Sci., 141, pp. L324
- Sandell, A., Björneholm, O., Nilsson, A., Zdansky, E., Tillborg, H., Andersen, J.N., Mårtensson, N., (1993) Phys. Rev. Lett., 70, p. 2000
- Nilsson, A., Tillborg, H., Mårtensson, N., (1991) Phys. Rev. Lett., 67, p. 1015
- Hochst, H., Brinngans, R.D., Steiner, P., Wolf, Th., (1982) Phy. Rev. B, 25, p. 7183
- Lahaye, J., Nanse, G., Bagreev, A., Strelko, V., (1999) Carbon, 37, p. 585
- Wei, Y.Y., Eres, G., Merkulov, V.I., Lowndes, D.H., (2001) Appl. Phys. Lett., 78, p. 1394
- Merkulov, V.I., Lowndes, D.H., Wei, Y.Y., Eres, G., (2000) Appl. Phys. Lett., 76, p. 3555
- Kim, H.S., Duy, D.Q., Kim, J.H., Lee, H.J., Yoon, D.M., Shin, S.S., Ha, J.W., Park, C.Y., (2008) J. Korean Phys. Soc., 52, p. 1057
- Wan, J., Luo, Y.H., Choi, S.D., Li, R.G., Jin, G., Liu, J.L., Wang, K.L., (2001) J. Appl. Phys., 89, p. 1973

- Lim, S.H., Kim, H.S., Lee, C.H., Pietruszko, S.M., Jang, J., (2002) *J. Non-Cryst. Solids*, 299-302, p. 864