

Structural and magnetic phase transitions of shape-memory Ni₅₀Mn_{25+x}Ga_{25-x} alloys with excess Mn

Thuy N.P., Nong N.V., Yao Y.D.

Faculty of Electronics and Telecommunication, College of Technology, Hanoi National University, Hanoi, Viet Nam; International Training Institute for Materials Sciences, Hanoi, Viet Nam; Institute of Physics, Academia Sinica, Taipei 115, Taiwan

Abstract: The Mn-excess Ni₅₀Mn_{25+x}Ga_{25-x} alloys with 1 < x < 7 were developed to investigate structural transitions and magnetic properties. The martensitic transformation temperature (T_M) for the structural transformation from tetragonal to cubic was clearly observed from magnetization, electrical resistivity and X-ray diffraction studies as a function of temperature for temperatures below 400 K. The T_M value increased roughly from 260 K to 355 K with increasing Mn concentration and T_M showed an abrupt change at the composition x = 5. For the structural transition, the Curie temperature (T_C) decreased slightly from 380 K and was insensitive to variations on the Mn/Ga ratio. During the heating and the cooling processes, the samples showed a temperature hysteresis at and below T_M . A magnetic-field-induced strain (MFIS) of about 0.2 % at an applied magnetic field of 4.2 kOe was derived by using the martensitic transition temperature for polycrystalline samples.

Author Keywords: Austenite; Field-induced strain; Martensite; Shape-memory alloy; Twin variants

Year: 2008

Source title: Journal of the Korean Physical Society

Volume: 52

Issue: 5

Page : 1478-1482

Link: Scopus Link

Correspondence Address: Thuy, N. P.; Faculty of Electronics and Telecommunication, College of Technology, Hanoi National University, Hanoi, Viet Nam; email: thuynp@vnu.edu.vn

ISSN: 3744884

Language of Original Document: English

Abbreviated Source Title: Journal of the Korean Physical Society

Document Type: Article

Source: Scopus

Authors with affiliations:

- Thuy, N.P., Faculty of Electronics and Telecommunication, College of Technology, Hanoi National University, Hanoi, Viet Nam
- Nong, N.V., International Training Institute for Materials Sciences, Hanoi, Viet Nam
- Yao, Y.D., Institute of Physics, Academia Sinica, Taipei 115, Taiwan

References:

- Webster, P.J., Ziebeck, K.R.A., Town, S.L., Peak, M.S., (1984) Philos. Mag. B, 49, p. 295

- Murray, S.J., Marioni, M., Allen, S.M., O'Handley, R.C., (2000) Appl. Phys. Lett, 77, p. 886
- Heczko, O., Sozinov, A., UUakko, K., (2000) IEEE Trans. Magn, 36, p. 3266
- Heczko, O., Jurek, K., UUakko, K., (2001) J. Magn. Magn. Mater, 226, p. 996
- Sozinov, A., Likhachev, A.A., Lanska, N., UUakko, K., (2002) Appl. Phys. Lett, 80, p. 1746
- Suorsa, I., Tellinen, J., Pagounis, E., Aaltio, I., Ullakko, K., (2002) 8th Int. Conf. on New Actuators, Actuator 2002, p. 158., Bremen, Germany
- Vasil'ev, A.N., Bozhko, A.D., Khovailo, V.V., (1999) Phys. Rev. B, 59, p. 1113
- Matsumoto, M., Takagi, T., Tani, J., Kanomata, T., Muramatsu, N., Vasil'ev, A.N., (1999) Mater. Sci. Eng. A, 273-275, p. 326
- Chernenko, V.A., Cesari, E., Kokorin, V.V., Vitcnko, I.N., (1995) Scripta. Metall. Mater, 33, p. 1239
- Jiang, C., Feng, G., Gong, S., Xu, H., (2003) Mater. Sci. Eng. A, 342, p. 231
- Mogylnyy, G., Glavatskyy, I., Glavatska, N., Soderberg, O., Ge, Y., Lindroos, V.K., (2003) Scripta Mater, 48, p. 1427