

Hard magnetic Fe-Pt alloys prepared by cold-deformation

Hai N.H., Dempsey N.M., Givord D.

Laboratoire Louis Néel, 25 avenue des Martyrs, 38042 Grenoble, France; Cryolab, Faculty of Physics, Vietnam National University, Hanoi, 334, Nguyen Trai, Thanh Xuan, Hanoi, Viet Nam; Laboratoire Louis Néel, C.N.R.S., B.P. 166, 3842 Grenoble-Cedex 9, France

Abstract: Tetragonal FePt is a ferromagnet with large magnetocrystalline anisotropy. The renewed interest in this system arises from possible applications, in particular for recording media and magnetic microsystems. FePt magnetic foils have been prepared by cyclic co-rolling of Fe and Pt foils down to the nm scale (total thickness of multilayer ≈ 100 nm), followed by heat-treatment in the temperature range 300°C to 700°C. The formation of the high anisotropy $L1_0$ FePt phase results from controlled diffusion and ordering. Coercivities of above 1 T are reached at room temperature following annealing at 450°C for 48 h. This is the highest value reported for bulk FePt. The differences between in-plane and out-of-plane magnetisation processes reveal that demagnetising fields are not simply proportional to the mean magnetisation. In Fe-rich FePt alloys, the hard FePt phase and the soft Fe_3Pt phase coexist. Out-of-plane magnetization reversal is described in terms of the dipolar-spring concept. © 2003 Elsevier Science B.V. All rights reserved.

Author Keywords: Bulk multilayers; Cold rolling; FePt magnets; Nanostructured magnetic materials

Index Keywords: Cold rolling; Deformation; Ferromagnetic materials; Heat treatment; Magnetic anisotropy; Magnetization; Nanostructured materials; Platinum; Thermal diffusion in solids; Cold-deformation; Iron alloys

Year: 2003

Source title: Journal of Magnetism and Magnetic Materials

Volume: 262

Issue: 3

Page : 353-360

Cited by: 20

Link: [Scopus Link](#)

Correspondence Address: Hai, N.H.; Laboratoire Louis Néel, C.N.R.S., B.P. 166, 3842 Grenoble-Cedex 9, France; email: hai@grenoble.cnrs.fr

Editors: Franse J.J.M.Duc N.H.Brommer P.R.

Conference name: Hanoi International Symposium

Conference date: 30 September 2002 through 30 September 2002

Conference location: Hanoi

Conference code: 61079

ISSN: 3048853

CODEN: JMMMD

DOI: 10.1016/S0304-8853(03)00062-3

Language of Original Document: English

Abbreviated Source Title: Journal of Magnetism and Magnetic Materials

Document Type: Conference Paper

Source: Scopus

Authors with affiliations:

- Hai, N.H., Laboratoire Louis Néel, 25 avenue des Martyrs, 38042 Grenoble, France, Cryolab, Faculty of Physics, Vietnam National University, Hanoi, 334, Nguyen Trai, Thanh Xuan, Hanoi, Viet Nam, Laboratoire Louis Néel, C.N.R.S., B.P. 166, 3842 Grenoble-Cedex 9, France
- Dempsey, N.M., Laboratoire Louis Néel, 25 avenue des Martyrs, 38042 Grenoble, France
- Givord, D., Laboratoire Louis Néel, 25 avenue des Martyrs, 38042 Grenoble, France

References:

- Kubaschewski, O., Fe-Pt binary phase diagram (1982) *Iron-Binary Phase Diagrams*, p. 91. , Springer, Berlin
- Kouvel, J.S., (1967) *Intermetallic Compounds*, p. 541. , J.H. Westbrook. New York: Wiley
- Cebollada, A., Farrow, R.F.C., Toney, M.F., (2002) *Magnetic Nanostructure*, p. 93. , H.S. Nalwa (Ed.), American Scientific
- Watanabe, K., Masumoto, H., (1984) *J. Jpn. Inst. Metals*, 48, p. 930
- Aboaf, J.A., McGuire, T.R., Herd, S.R., Klokholm, E., (1984) *IEEE Trans. Magn.*, 20, p. 1642
- Coffey, K.R., Parker, M.A., Howard, J.K., (1995) *IEEE Trans. Magn.*, 31, p. 2737
- Ristau, R.A., Barmak, K., Lewis, L.H., Coffey, K.R., Howard, J.K., (1999) *J. Appl. Phys.*, 86, p. 4527
- Cebollada, A., Weller, D., Sticht, J., Harp, G.R., Farrow, R.F.C., Marks, R.F., Savoy, R., Scott, J.C., (1994) *Phys. Rev. B*, 50, p. 3419
- Shima, T., Takanashi, K., Takahashi, Y.K., Hono, K., (2002) *Appl. Phys. Lett.*, 81, p. 1050
- Levi, F.P., (1960) *J. Appl. Phys.*, 31, p. 1469
- Van-Bockstal, L., Harrison, N., Liang, L., Herlach, F., Dupouy, F., Askenazy, S.F., (1995) *Physica B*, 211, p. 65
- Yasuna, K., Terauchi, M., Otsuki, A., Ishihara, K.N., Shingu, P.H., (1997) *J. Appl. Phys.*, 82, p. 2435
- Wacquant, F., Denolly, S., Giguère, A., Nozières, J.P., Givord, D., Mazaauric, V., (1999) *IEEE Trans. Magn.*, 35, p. 3484
- Giguère, A., Hai, N.H., Dempsey, N.M., Givord, D., (2002) *J. Magn. Magn. Mater.*, 242-245, p. 581
- Giguère, A., Dempsey, N.M., Verdier, M., Ortega, L., Givord, D., (2002) *IEEE Trans. Magn.*, 38, p. 2761
- Honeycombe, R.W.K., (1968) *The Plastic Deformation of Metals*, p. 325. , Edward Ltd
- Hai, N.H., Dempsey, N.M., Veron, M., Verdier, M., Givord, D., (2003) *J. Magn. Magn. Mater.*, 257, p. 139
- Givord, D., David, S., Hai, N.H., Dempsey, N.M., Toussaint, J.C., (2002) *Proceedings of the 17th International Workshop on Rare Earth Magnets and Their Applications (Supplement)*, p. 1058. , August 18-22, Newark, Delaware, USA
- Givord, D., Rossignol, M., (1996) *RE-Fe Permanent Magnets*, p. 218. , J.M.D. Coey. Oxford: Clarendon press
- Liu, J.P., Kuo, C.P., Liu, Y., Sellmyer, D.J., (1998) *Appl. Phys. Lett.*, 72, p. 483
- Givord, D., Hai, N.H., Toussaint, J.C., to be submitted

Download: 0838.pdf